



**Rosenfeld
Kidson**

SPECIES FACT SHEET



European White Oak – *Quercus spp.*

OTHER NAMES: French Oak, English Oak etc. (according to origin),
Rovere, Quercia, Chene

REGION OF ORIGIN: Central Europe



GENERAL DESCRIPTION

European Oak heartwood is light tan to biscuit colour and usually straight grained but irregular or cross-grained material can occur. Characteristic silver grain figure on quartered surfaces due to broad rays.

MAIN USES

Furniture and cabinetmaking, interior joinery, flooring, wine barrel staves and caskets.

WORKING PROPERTIES

There is moderate to severe blunting on cutters.
The wood takes waxing, liming, fuming and polishing treatments very well.

MECHANICAL PROPERTIES

Oak has a very good steam bending classification, but is liable to blue stain if in contact with iron compounds.

AVAILABILITY

Specifications stocked at Rosenfeld Kidson are:
Sawn 225x25mm, ex 225x25mm T&G strip flooring.
25, 40 and 50mm thicknesses in random widths.

GRADING

Prime (FAS), Light Feature.

DENSITY (kg/m³)*:	720
DURABILITY:	Durable

STRENGTH GROUP:	SD5
MOR (MPa):	105
MOE(GPa):	13.3
JANKA(kN):	5.9

SHRINKAGE GREEN TO 12% M.C.	Tangential	Radial
	9.7	4.5

*Air Dry Density (kg/m³) is average indication only and actual value may vary. Refer to timber properties tables over page for strength, shrinkage and durability classifications.

E: rk@rosenfeldkidson.co.nz
W: www.rosenfeldkidson.co.nz
www.cedarscreen.co.nz

Auckland:
T: +64 9 573 0503
F: +64 9 573 0504
513 Mount Wellington Highway,
Mount Wellington,
Auckland 1060

Christchurch:
T: +64 3 349 3316
F: +64 3 349 3317
15 Edmonton Road, Hornby,
Christchurch 8042

Postal Address: P O Box 621,
Shortland Street, Auckland 1140



**Rosenfeld
Kidson**

TIMBER PROPERTIES

STRENGTH GROUPINGS

Minimum values for strength groups (unseasoned timber)			
(units are Mpa = 145 lb/sq.inch)			
Strength group	Modulus of rupture	Modulus of elasticity	Maximum crushing strength
S1	103	16300	52
S2	76	14200	43
S3	73	12400	36
S4	62	10700	31
S5	52	9100	26
S6	43	7900	22
S7	36	6900	18

Minimum values for strength groups (seasoned timber)			
(units are Mpa = 145 lb/sq.inch)			
Strength group	Modulus of rupture	Modulus of elasticity	Maximum crushing strength
SD1	150	21500	80
SD2	130	18500	70
SD3	110	16000	61
SD4	94	14000	54
SD5	78	12500	47
SD6	65	10500	41
SD7	55	9100	36
SD8	45	7900	30

SHRINKAGE CLASSIFICATIONS

Description of shrinkage	Shrinkage from Green to Oven-dry (12% MC)	
	(%) before reconditioning	
	Tangential	Radial
Very Low	0 - 3.5	0 - 2
Low	3.5 - 5.0	2 - 3
Medium	5.0 - 6.5	3 - 4
High	6.5 - 8.0	4 - 5
Very High	> 8.0	> 5

DURABILITY CLASSIFICATIONS

Grade of durability	Approximate service life (years)		
	Fully Protected	Above ground, exposed	In-ground, exposed
Very Durable	> 50	> 40	> 25
Durable	> 50	15 - 40	15 - 25
Moderately Durable	> 50	7 - 15	5 - 15
Non-Durable	> 50	0 - 7	0 - 5

E: rk@rosenfeldkidson.co.nz
W: www.rosenfeldkidson.co.nz
 www.cedarscreen.co.nz

Auckland:
T: +64 9 573 0503
F: +64 9 573 0504
 513 Mount Wellington Highway,
 Mount Wellington,
 Auckland 1060

Christchurch:
T: +64 3 349 3316
F: +64 3 349 3317
 15 Edmonton Road, Hornby,
 Christchurch 8042

Postal Address: P O Box 621,
 Shortland Street, Auckland 1140